

PRODUCT MANUAL FOR GROUND GRANULATED BLAST FURNACE SLAG FOR USE IN CEMENT, MORTAR AND CONCRETE ACCORDING TO IS 16714: 2018

This Product Manual shall be used as reference material by all Regional/Branch Offices & licensees to ensure coherence of practice and transparency in operation of certification under Scheme-I of Bureau of Indian Standards (Conformity Assessment) Regulations, 2018 for various products. The document may also be used by prospective applicants desirous of obtaining BIS certification licence/certificate.

1.	Product	:	IS 16714 : 2018					
	Title	:	GROUND GRANULATED BLAST FURNACE SLACE FOR USE IN CEMENT, MORTAR AND CONCRETE					
	No. of Amendments	:	NIL					
2.	Sampling Guidelines:							
a)	Raw material	:	-					
b)	Grouping guidelines	:	NA					
c)	Sample Size	:	For Physical test – 8 kg For Chemical test – 1 kg					
3.	3. List of Test Equipment : Please refer ANNEX – A							
4.	Scheme of Inspection and Testing	:	Please refer <u>ANNEX – B</u>					
5.	Possible tests in a day :							
	(i) Fineness (Clause 6) (ii) Moisture content (Clause 5.2) (iii) Loss on ignition (Clause 5.1) (iv) Insoluble residue (Clause 5.1)							
6.	Scope of the Licence:							
	"Licence is granted to use Standard Mark on Ground Granulated Blast Furnace Slag for Use in Cement, Mortar and Concrete as per IS 16714: 2018.							

BUREAU OF INDIAN STANDARDS

Manak Bhawan, 9, Bahadur Shah Zafar Marg,

New Delhi – 110002

ANNEX A

List of Test Equipment

Major test equipment required to test as per the Indian Standard

S. No.	Tests used in with Clause	Test Equipment					
	Reference	Plaine's amountus variable flavortones					
1	Fineness	Blaine's apparatus variable flow type					
	Clause 6 Table 2	Stop watch with start-stop mechanism					
		Mercury for calibration					
		Balance, Standard weights					
		Standard Cement					
		Manometer liquid (di-butyl phthalate or light					
		mineral oil.) Mercury of reagent grade or better Pyknometer					
		Mercury of reagent grade or better, Pyknometer					
		Circular discs of filter paper of medium porosity					
		(mean pore diameter 7μ).					
		Le-Chatelier's flask					
		Constant temperature water bath to maintain					
		temperature within \pm 0.1 $^{\circ}$ C					
2	Slag Activity Index	Vibration machine with timer & cube mould fitting					
	Clause 6 Table 2	assembly 12000 ± 400 vibration per min.					
		Compressive Strength machine					
		Poking Rod, Petroleum Jelly					
		Proving ring with all accessories suitable for					
		calibration of CST machine					
		Tachometer					
		Cube Moulds 70.6×70.6 mm, Poking rod					
		Gauging trowel $(210 \pm 10 \text{ g})$					
		gauging plate, stainless steel(non-perforated)					
		Standard sand (as per IS 650)					
		Curing tank of appropriate size with water					
		circulation arrangement					
		Graduated glass cylinders 150 to 200 ml					
		Humidity chamber with temperature & RH					
		Control 27 ± 2° C, RH 90 to 100 %					
		Vicat apparatus					
		Needle for Consistency testing					
		Moulds Stop Watch					
		Sup walli					

3	IS 16714 : 2018	General equipments for Cement testing				
	To control humidity & temperature in lab	 Humidity chamber with temperature & RH control 27 ± 2 °C, RH 90 to 100 % Suitable arrangement to demonstrate maintenance of temperature of 27 ± 2 °C & RH 65 ± 5% constantly 				
	For cement Sampling	Mixing trays –adequate size including trays of 24 partitions for keeping hourly samples				
	To control the residue of cement	Sieves of size (300, 212, 150, 90, 75 & 45µ)				
	To measure temperature	Thermometers				
	Lab ball mill (motorized)	To grind the clinker, slag & gypsum sample in lab ball mill for testing				
	To weigh the material	Platform type balance Electrical balance Weight box with weights (1 mg - 500 g)				
4	General test equipments for	Heater and hot plate				
	chemical testing Clause 5.1 , Table 1 of	Distillation Assembly				
	IS 16714 : 2018	Crucible: Platinum or Porcelain / silica				
		Filter paper (No- 1, 40, 41, 42)				
		Desiccators with cover & Desiccant				
		Water bath				
		pH meter/paper				
		Glassware - volumetric flask -0-250 ml, beaker 0-250 ml, measuring cylinder 0-50,100,500, 1000 ml, burette 0-25/50 ml, conical flasks- 0-250 ml, pipette 0-5,10, 25, 50 ml Erlenmeyer flask Gas generating flask, etc				
		All chemicals required for complete chemical analysis of cement				
		Tongs including platinum tipped tong				
		Wire gauge with asbestos sheet at the middle				
		Washing bottle				
		Mortar mixer- 4.75 l Glass thermometer				

PM/ IS 16714/ 1/ March 2019

		All required chemicals as per IS 4032 for Ground Granulated Blast Furnace Slag testing
5	Moisture content (Clause 5.2)	Petri dish Oven Weighing balance Desiccator
6	Glass content (Clause 5.3)	Optical microscope min 100 X Bromoform IS sieve 90 and 52 microns Weighing balance Rectangular glass side

The above list is indicative only and may not be treated as exhaustive.

ANNEX B

Scheme of Inspection and Testing

- **1. LABORATORY** A laboratory shall be maintained which shall be suitably equipped (as per the requirement given in column 2 of Table 1) and staffed, where different tests given in the specification shall be carried out in accordance with the methods given in the specification.
- **1.1** The manufacturer shall prepare a calibration plan for the test equipment. However calibration of following test equipments shall be carried out at a frequency shown against each and record of same shall be kept.

Sl. No.	TEST EQUIPMENT	FREQUENCY OF CALIBRATION					
1	Blaine's apparatus	Daily with licensee's own Standard cement sample and					
		monthly with standard cement samples supplied by					
		NCCBM.					
2	Compressive	Once in a month with Licensee's own Proving Ring and					
	strength Testing	the Proving Ring shall be Calibrated once in two years					
	machine	from a NPL/NABL Accredited Calibrating body or NPL					
		or NPL accredited Proving Ring manufacturer.					
3	Vibration machine	Once in a month by licensee's own Tachometer. The					
		tachometer shall be calibrated once in a year from					
		NPL/NABL accredited outside agency.					

- **2. TEST RECORDS** The manufacturer shall maintain test records for the tests carried out to establish conformity.
- 3. LABELLING AND MARKING As per the requirements of IS 16714: 2018
- **4. CONTROL UNIT** Entire quantity of Ground granulated blast furnace slag produced from same source of granulated blast furnace slag in a week shall constitute a control unit.
- **5. LEVELS OF CONTROL** The tests as indicated in column 1 of <u>Table 1</u> and the levels of control in column 3 of <u>Table 1</u>, shall be carried out on the whole production of the factory which is covered by this plan and appropriate records maintained in accordance with paragraph 2 above.
- **5.1** All the production which conforms to the Indian Standard and covered by the licence should be marked with Standard Mark.
- **5.2 PACKING** Packing of Ground granulated blast furnace slag shall be done as per clause 7 of IS 16714 : 2018.
- **5.3 WEIGHMENT** One filled bag from each nozzle shall be taken at random twice in each shift of operation and weight checked in case of electronic packers with recorders. In all other cases one filled bag from each nozzle shall be checked once in two hours. The bag shall be so

chosen for weighment such that bags from each nozzle are taken for weighment. The weighing and packing machines shall be adjusted as and when necessary in such a way that net quantity of each bag shall be in accordance with the tolerances given clause 7.2.1 of IS 16714: 2018. Such adjustments for each nozzle shall be recorded.

- **5.3.1** For packing of Ground granulated blast furnace slag in bulk cement terminal weighment of hourly check of mass of drums also shall be done in addition to weighment of bags mentioned in para 5.3 above. The records of weighments shall be maintained.
- **6. REJECTIONS** Disposal of non-conforming product shall be done in such a way so as to ensure that there is no violation of provisions of BIS Act, 2016.

TABLE 1

	(1)			(2)			(3)	
Test Details				Test equipment		Levels of Control		
Cl.	Requirement	Test Methods		requirement	Number	Number Frequency		Remarks
		Clause	Reference	R: required (or) S: Sub-contracting permitted	of sample	Grinding stage	Packing stage	
5.1 & Table 1	Chemical requirements							
i)	Manganese oxide	5.1	IS 4032	R	One	Daily Composite sample	Weekly composite sample	-
ii)	Magnesium oxide	5.1	IS 4032	R	One	Daily Composite sample	Weekly composite sample	-
iii)	Sulphide sulphur	5.1	IS 4032	R	One	Daily Composite sample	Weekly composite sample	-
iv)	Sulphate as SO ₃	5.1	IS 4032	R	One	Daily Composite sample	Weekly composite sample	-
v)	Insoluble residue	5.1	IS 4032	R	One	Daily Composite sample	Weekly composite sample	-
vi)	Chloride content	5.1	IS 4032	R	One	-	Weekly composite sample	-
vii)	Loss on ignition	5.1	IS 4032	R	One	Daily Composite sample	Weekly composite sample	-
viii)	$\frac{CaO + MgO + \frac{1}{3}AlO_3}{SiO_2 + \frac{2}{3}AlO_3}$	5.1	IS 4032	R	One	Daily Composite sample	Weekly composite sample	-
ix)	$\frac{CaO + MgO + Al_2 O_3}{Si O_2}$	5.1	IS 4032	R	One	Daily Composite sample	Weekly composite sample	-
x)	$\frac{CaO + CaS + \frac{1}{2}MgO + Al_2 O_3}{Si O_2 + MnO}$	5.1	IS 4032	R	One	Daily Composite sample	Weekly composite sample	For slag with MnO >2.5 % only
5.2	Moisture content	5.2 Annex – B	IS 16714	R	One	Daily Composite sample	Weekly composite sample	-
5.3	Glass content	5.3 Annex – C	IS 16714	S	One	Alternate control unit	Alternate control unit	-

6 & Table 2	Physical requirements							
i)	Fineness	6	IS 4031 (Part 2)	R	One	Every alternate hourly from each mill separately. Daily Composite sample	Daily Composite sample	-
ii)	Slag activity index	6	IS 4031 (Part 6)	R	One	Daily Composite sample	Daily Composite sample	-

Note-1: Composite sample shall be made out of hourly samples for the required period (Pl see IS 3535 Methods of sampling hydraulic cements). If slag is manufactured using same raw materials from more than one grinding mill, sample from each mill shall be tested for fineness as per the above table. For all other parameters composite samples from all the mills shall be tested. If slag is manufactured using different source of raw materials from more than one grinding mill, sample from each mill shall be tested for all requirements as per the above table.

Note 2: For manufacturing units where there is no packing silo and slag is packed directly from grinding mill, the frequency of tests specified for grinding stage would apply for the various tests to be carried out on samples taken from packing spouts along with weekly chloride content test.

Note- 3 : Sub-contracting is permitted to a laboratory recognized by the Bureau or Government laboratories empanelled by the Bureau.

Note- 4: Levels of control given in column 3 are only recommendatory in nature. The manufacturer may define the control unit/batch/lot and submit his own levels of control in column 3 with proper justification for approval by BO Head.